

Lip Gloss Gel

(Sample recipe for Polyamide 3)

Lip Gloss Gel

Phase A	Weight %	For 100 g / 8.5 oz
Castor Oil (emollient)	60 %	60 g / 2.1 oz
Macadamia Nut Oil (emollient)	20 %	20 g / 0.7oz
Polyamide 3 (thickener)	20 %	20 g / 0.7oz
Mica Color	As desired %	

Method

Add Phase A into a clean and disinfected glass beaker. Stir and heat to 75C/170F until Polyamide 3 is completely melted. Add mica color if desired, stir and fill into lip balm tubes.

Properties

Excellent feel, stability and wear. Can be used as clear gloss stick or made with color.