

## Spring Colored Eye Shadow

(Sample Recipe for Chromium Oxide Green)

### Spring Colored Eye-Shadow

| Phase A              | Weight % | For 20 g /0.7 oz |
|----------------------|----------|------------------|
| Mineral Base         | 79 %     | 16.2 g / 0.6 oz  |
| Magnesium Stearate   | 5 %      | 1 g / 1/2 tsp    |
| <b>Phase B</b>       |          |                  |
| Ultramarine Blue     | 4 %      | 0.8 g / 1/4 tsp  |
| Chromium Oxide Green | 2 %      | 0.2 g / 1/8 tsp  |
| <b>Phase C</b>       |          |                  |
| Mica Patina Silver   | 10 %     | 2 g / 1 tsp      |

#### Method

Give Phase A into a clean mortar and blend well with the pestle.

Add phase B to Phase A and blend well with the pestle or divide Phase A to make multiple colors.

When Phase C is added the pestle should not be used anymore.

Diamond Cluster can also be used instead of the patina silver or in combination to give more sparkle.

The proportions of the colors can be changed, by adding more to create more intense shades or less for lighter pastel shades.

#### Properties

Loose eye shadow to be used with small shaker/sifter jars.