

1326 - Matte Lipstick (50.00g)

| Ingredient | Function | Percent | Wgt (g) | Wgt (oz) | Vol (tsp.) |
|--|-------------|---------|---------|----------|------------|
| Phase A | | | | | |
| Octyldodecanol (octyldodecanol) | Emollient | 22.00 | 11.00 | 0.39 | 2.20 |
| Silica (silica) | Texturizer | 2.00 | 1.00 | 0.04 | 0.20 |
| Microcrystalline Wax (microcrystalline wax) | Thickener | 6.00 | 3.00 | 0.11 | 0.60 |
| Synthetic Wax (synthetic wax) | Thickener | 9.00 | 4.50 | 0.16 | 0.90 |
| Bees Wax (cera alba [bees wax]) | Thickener | 5.00 | 2.50 | 0.09 | 0.50 |
| Kaolin (kaolin) | Texturizer | 2.00 | 1.00 | 0.04 | 0.20 |
| Vitamin E Tocopherol (dl-alpha tocopherol) | Antioxidant | 0.20 | 0.10 | 0.00 | 0.02 |
| Jobba Oil, Organic (Simmondsia Chinensis [Jojoba] seed oil) | Emollient | 5.00 | 2.50 | 0.09 | 0.50 |
| Carnauba Wax (copernicia prunifera [carnauba] wax) | Thickener | 5.00 | 2.50 | 0.09 | 0.50 |
| Phase B | | | | | |
| Red No. 40 FD&C Lake (CI 15850 [red no. 40 FD&C lake]) | Colorant | 0.50 | 0.25 | 0.01 | 0.05 |
| Red No. 28 Lake CI 45410 (red no. 28 D&C lake) | Colorant | 1.00 | 0.50 | 0.02 | 0.10 |
| Mica Sugar Blush (mica [CI 77019], titanium dioxide [CI 77891], iron oxide [CI 77491]) | Colorant | 4.00 | 2.00 | 0.07 | 0.40 |
| Mica Blackstar Red (mica [CI 77019], iron oxide [CI 77491]) | Colorant | 2.00 | 1.00 | 0.04 | 0.20 |
| Titanium Dioxide For Makeup, Liquid (titanium dioxide, octyldodecanol) | Colorant | 3.00 | 1.50 | 0.05 | 0.30 |
| Phase C | | | | | |
| Silicone Resin (trimethylsiloxy silicate, polypropyl silsesquioxane) | Film-Former | 7.00 | 3.50 | 0.12 | 0.70 |
| Isododecane (isododecane) | Emollient | 26.30 | 13.15 | 0.46 | 2.63 |

Method

Start with phase C. Dissolve the silicone resin in the isododecane, under stirring, heating slightly will help dissolving. Allow about 10min under constant stirring. Combine phase A in a heat resistant glass beaker. Add phase B to it and stir well. Heat slowly to 75C/80C, until all waxes are melted. Add phase C slowly to phase A/B, under stirring. Test a drop of color & make adjustments. When color is uniform, pour into mold and cool.

Properties

Matte lipstick in solid form that leaves a medium matte finish. *color choices: mica sugar blush will give a warmer shade and "mica blackstar red, a cooler shade. If you prefer just one mica use 6% total or leave as is using both. Many different color combinations are possible.