

**Soft Matte Lip Color - 100g/3.6oz - 1255**

<b>Ingredient</b>	<b>Function</b>	<b>Percent</b>	<b>Wgt (g)</b>	<b>Wgt (oz)</b>	<b>Vol (tsp.)</b>
<b>Phase A</b>					
Silicone Resin (trimethylsiloxy silicate, polypropyl silsesquioxane)	Film Former	10.00	10.00	0.18	1.00
Isopropyl Myristate (isopropyl myristate)	Emollient	37.50	37.50	0.66	3.75
Brassica Glycerides (brassic glycerides)	Thickener	5.00	5.00	0.09	0.50
Polyhydroxystearic Acid (Polyhydroxystearic Acid)	Thickener	3.00	3.00	0.05	0.30
Candelilla Wax (Euphorbia Cerifera [candelilla] wax)	Thickener	13.00	13.00	0.23	1.30
Vitamin E Tocopherol (dl-alpha tocopherol)	Antioxidant	0.50	0.50	0.01	0.05
Mango Butter (Mangifera Indica [Mango] seed butter)	Emollient	2.00	20.00	0.04	0.20
Lauryl Laurate (lauryl laurate)	Emollient	2.00	2.00	0.04	0.20
Microcrystalline Wax (microcrystalline wax)	Thickener	4.00	4.00	0.07	0.40
<b>Phase B</b>					
Titanium Dioxide For Makeup, Liquid (titanium dioxide, octyldodecanol)	Colorant	3.00	3.00	0.05	0.30
Mica Sappan Red (mica [CI 77019], tin oxide [CI 77861], titanium dioxide [CI 77891], Caesalpinia Sappan bark extract)	Colorant	0.70	0.70	0.01	0.07
Color Blend (various colors)	Colorant	5.30	5.30	0.09	0.53
Kaolin (kaolin)	Mattifier	10.00	10.00	0.18	1.00
Caprylyl Glycol EHG (caprylyl glycol, ethylhexylglycerin)	Anti-Microbial	1.00	1.00	0.02	0.10
Silica (silica)	Texturizer	3.00	3.00	0.05	0.30

**Method**

Add Isopropyl Myristate to a heat-resistant beaker and heat to 50 - 60C. Add Silicone Resin very slowly, stirring well and adding more as it dissolves. Once all the resin has dissolved (this should take 5 - 10 minutes), remove beaker from heat. Add remaining phase A ingredients and return to heat, and heat to 70C to melt all of the waxes. Stir well. Remove from heat, and add phase B ingredients and stir well. Pour into lipstick mold and allow to fully cool.

**Properties**

A soft, comfortable matte lipstick that has great payoff and wearing time. Contains Mango Butter to moisturize the lips and Silica to give a silky feel. Color Blend : Lipstick example (darker red): (for 100/3.6oz grams of lipstick): 0.7g Mica Blackstar Red, 0.7g Sappan Red, 1.2g Mica Bordeaux, 3.4g Red 40 powder.